(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau

(43) International Publication Date
15 March 2001 (15.03.2001)

PCT

(10) International Publication Number
WO 01/17571 A1

(51) International Patent Classification[7]: A61L 27/34, 27/58

(21) International Application Number: PCT/GB00/03343

(22) International Filing Date:
1 September 2000 (01.09.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
9920732.6 3 September 1999 (03.09.1999) GB

(71) Applicant *(for all designated States except US)*: **SULZER VASCUTEK LIMITED** [GB/GB]; Newmains Avenue, Inchinnan, Renfrewshire PA4 9RR (GB).

(72) Inventor; and
(75) Inventor/Applicant *(for US only)*: **KELSO, Karen, Anne** [GB/GB]; 4 Dalgarven Mews, Kilmarnock KA3 6BJ (GB).

(74) Agent: MURGITROYD & COMPANY; 373 Scotland Street, Glasgow G5 8QA (GB).

(81) Designated States *(national)*: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States *(regional)*: ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:
— *With international search report.*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 01/17571 A1

(54) Title: SEALANT FOR VASCULAR PROSTHESES

(57) Abstract: There is described a bioresorbable sealant or coating for a prosthetic graft. The novel sealant described is based upon dextran, preferably obtained by microbial fermentation, cross-linked through reaction with formaldehyde and urea. The breakdown products of the sealant or coating are all of low molecular weight and may be easily processed by the body. A method of producing the novel sealant or coating is also described.

SEALANT FOR VASCULAR PROSTHESES

The present invention relates to a non-gelatine based coating or sealant for porous vascular prostheses, and to a method of making that coating or sealant.

Porous vascular prostheses constructed from textiles (such as polyester) are normally woven or knitted and ultimately rely on host tissue penetrating into the spaces between the yarns. To function in the long term the prostheses must, therefore, acquire porosity whilst at implant bleeding through the prosthesis wall must be prevented or at least limited to an acceptable level.

In the past this dilemma has been resolved by soaking a porous textile-based prosthesis in the patient's blood which then clots to form a seal. This pre-clotting technique is time consuming, exposes the prosthesis to potential contamination and may be ineffective in patients with reduced clotting ability (either reduced

spontaneous blood clotting or through administration of anti-platelet or anti-thrombotic medication).

More recently, vascular prostheses have been pre-sealed with a variety of bioresorbable materials. The sealants tried to date have tended to be protein based, such as collagen, gelatin or albumen. Cross-linkers such as glutaraldehyde, formaldehyde, carbodiiamide or isocyanates have been used to render the proteins insoluble and mention may be made of EP-B-0,183,365; US-A-4,747,848 and US-A-4,902,290, all of which describe the preparation of cross-linked gelatin-based sealants. Hydrolysis or enzymatic attack in the host tissue has then gradually degraded or removed the sealant from the textile to permit the necessary tissue ingrowth.

The prior art protein based sealants are derived from animal or human sources, which creates the potential for transmission of infection. This has been especially of concern following transmission of BSE to humans which has greatly elevated public concern over the safety of animal derived implants. Additionally, although some materials, such as gelatin, are produced in large commercial quantities and blended to give high lot-to-lot consistency, manufacture from natural raw materials always has the potential for variability which creates uncertainty regarding performance of the graft.

The present invention relates to a bioresorbable sealant which is not animal derived but is based on

cross-linked dextran. Dextran is produced by a fermentation process using *Leuconostoc mesenteroides* bacteria growing on a sugar-based energy source, such as sucrose. Partial hydrolysis of the fermentation product yields dextrans of defined molecular weight. These have been used widely as plasma substitutes with a typical molecular weight of 40,000.

Dextrans of this molecular weight are freely water-soluble. To form a useful graft sealant, the dextrans must be rendered insoluble. However, dextrans are not easily cross-linked as they have limited reactive sites to form intermolecular bonds. The available groups are almost exclusively hydroxyl (OH) groups.

British Patent No 854,715 describes the formation of a dextran-based polymer by using epichlorohydrin. However the epichlorohydrin-based approach forms very stable cross-links so that the resultant polymer is resistant to both enzymatic and hydrolytic attack and does not biodegrade. Epichlorohydrin cross-linked dextran is, therefore, unsuitable as a vascular graft sealant as it is not bioresorbable and would not permit tissue ingrowth within the timescale required. EP-B-0,183,365 and US-A-4,747,848 both describe a gelatin-based sealant in which the time-scale of reabsorption is controllable.

To overcome this problem, a novel dextran-based polymer has been produced which is bioresorbable through hydrolysis in the time scale of interest.

The present invention provides a bioresorbable sealant composition comprising a polymer formed by reaction between dextran, formaldehyde and urea. Whilst the dextran polymer product is insoluble, the polymer is formed with bonds that are sufficiently labile to permit resorption at an appropriate rate for tissue ingrowth. Furthermore, when the cross-linked polymer breaks down, it does so into simple products all of which have a low molecular weight and which are easy for the body to dispose of.

The term "dextran" as used herein includes naturally occurring dextran (especially that obtained through fermentation of micro-organisms such as *Leuconostoc sp.*) as well as hydrophilic hydroxyl group-containing derivatives of dextran, for example partially depolymerized dextran, dextran glycerine glycoside or hydrodextran. Also included are modified forms of dextran containing other reactive groups, for example carboxyl, sulphonic, sulphate, amino or substituted amino groups. Mention may be made of carboxymethyldextran and dextran sulphate as examples of modified dextran. Mixtures of different dextrans (as defined herein) may of course also be used, where appropriate.

The polymer described herein is formed in water or an aqueous-based solvent. It is therefore essential that the dextran selected as the initial reactant should be water-soluble or in the form of swollen particles.

Dextrans having a molecular weight of 10,000 to 100,000, in particular 20,000 to 80,000, especially 30,000 to 60,000 may be used. Preferably the dextran used in the invention has a typical molecular weight of about 40,000.

Viewed from one aspect, therefore, the present invention provides a method of forming polymerised dextran for use as a biodegradable coating for a prosthetic graft, said method comprising:

a) exposing a water-based solution of dextran to 2 to 25 (weight %) of urea and allowing the urea to enter into solution to form a mixture;

b) exposing the mixture of step a) to formaldehyde;

c) heating the mixture of step b) at temperatures between 20 to 250°C for a time sufficient to allow polymerisation to occur.

The formaldehyde is conveniently added in the form of formalin (a 37% aqueous solution of formaldehyde hydrate). Alternatively, it would be possible to bubble formaldehyde gas through the mixture of step (a) to achieve the required reaction. The quantity of formaldehyde required may be determined stochiometrically having regard to the amount of urea added in step (a). We have found that an amount of formaldehyde equivalent to 50 to 100% (by weight) with reference to the amount of urea achieves the required

result, with 70 to 80% (by weight) being preferred. Usually a time period of from five to 60 minutes is sufficient to permit the cross-linking reaction to occur.

In a further aspect, the present invention provides a method of producing a non-porous graft by impregnating or coating a flexible material with a mixture of dextran, urea and formaldehyde, and incubating said impregnated material at temperatures of from 20°C to 250°C for a time sufficient to facilitate cross-linking of said dextran. The flexible material to be impregnated or coated will usually be a macroporous (eg a knitted or woven) fabric. However, non-porous or microporous materials may likewise be coated, with the sealant reducing blood loss after suturing.

Preferably the temperature selected is from 30°C to 200°C, for example is from 45°C to 160°C.

The flexible porous material to be treated by the present invention may be of any conventional type or construction. Particular mention may be made of polyester (e.g. DACRON™) knitted or woven fabric and also of PTFE-based materials. Additionally, expanded PTFE may be coated as described since, although the material itself is non-porous, porosity will be introduced when the graft is stitched into place by the surgeon. The graft may be simply immersed in the reaction mixture or may be selectively dipped therein (for example the graft may be placed on a mandrel and

"rolled" over the surface of the reaction mixture to coat the external surface only). Optionally pressure may be used to ensure penetration of the reaction mixture into the interstices of a porous graft.

In a further aspect, the invention also provides a prosthetic graft impregnated or coated with the bioresorbable sealant of the invention. The graft may be, for example, a knitted polyester graft.

To prevent the sealant from drying out on the graft and becoming brittle in storage it is advantageous to plasticise the treated graft with a biocompatible agent such as glycerol. This is preferably achieved by treating the sealed grafts with glycerol after cross-linking of the dextran. Excess glycerol may be removed by alcohol rinsing. Suitable alcohols include ethanol, methanol and propanol, but other alcohols may also be used.

As described above, the treated graft may be plasticised. Alternatively, or additionally, the graft may undergo a separate sterilisation step, for example by exposure to γ-irradiation. Sterilisation may not be required if the graft and coating have been formed in sterile conditions.

The primary mechanism of polymerisation involves a urea/formaldehyde condensation reaction, where the application of high temperature and water encourages polymerisation of the dextran reactant. Subsequent

condensation reactions involve primary hydroxyl groups present on the dextran molecule. Due to the small levels of urea and formaldehyde required to cause the reactions it was believed the process needed only short urea-formaldehyde condensate links to give good cross-linking parameters. Subsequently formed bonds were identified as reactive ether bonds which were subject to hydrolytic degradation. Various forms of analysis such as NMR and FTIR have confirmed that the degradation products are of low molecular weight and likely to comprise sugar units, urea, formaldehyde and small complexes of the latter components. It is of course possible to modify the hydroxyl groups available on the dextran for reaction (see for example EP-B-0,183,365).

The use of dextran sulphate is desirable since the cross-linked polymer so produced contains sulphate groups available for binding, for example, to the heparin binding site of fibroblast growth factor. Fibroblast growth factors form a large family of structurally related, multifunctional proteins that regulate various biological responses and have been implicated in many developmental and regenerative events including axial organisation, mesodermal patterning, keratinocyte organisation and brain development. These compounds mediate cellular functions by binding to transmembrane fibroblast growth factor receptors, which are protein tyrosine kinases. Fibroblast growth factor receptors are activated by oligomerisation and both this activation and fibroblast growth factor stimulated biological responses, require

the presence of "heparin-like" molecules as well as fibroblast growth factor.

Heparins are linear polysaccharide chains; they are typically heterogeneously sulphated on alternating L-iduronic and D-glycosamino sugars. A review of the fibroblast growth factor molecular complexes associated with heparin-like sugars has recently been undertaken (DiGabriele et al., 1998; ISSN 0028-0836). Heparin sulphates, the N-sulphated polysaccharide components of proteoglycans, are common constituents of cell surfaces and the extracellular matrix. The heparin sulphate polysaccharide chain has a unique molecular design in which the clusters of N and O-sulphated sugar residues, separated by regions of low sulphation, determine specific protein binding properties. Current data indicates that relatively long specific binding sequences of heparin sulphate may induce a conformational change in basic fibroblast growth factor, exposing a site on the protein that is recognised by signal transducing receptors. There are also suggestions that the core protein of plasma membrane heparin sulphate-proteoglycans may participate in the cell signalling process (Gallagher, 1994; ISSN 0939-4974).

The heparin sulphate chains are attached to various protein cores, which determine the location of the proteoglycan in the cell membrane and extracellular matrix. The diverse functions of heparin sulphate, which range from the control of blood coagulation to the regulation of cell growth and adhesion, depend on

the capacity of the chains to activate protein ligands, such as antithrombin III and members of the fibroblast growth factor family. These properties are currently being exploited in the development of synthetic heparin sulphates as anticoagulants and promoters of wound healing. Conversely organic mimics of growth factor-activating saccharides could possibly be designed to suppress tumour growth and prevent restenosis after coronary vessel angioplasty (Stringer and Gallagher, 1997; ISSN 1357-2725). Earlier researchers had also reported on the theory that fibroblast growth factor receptors might be directly activated by a much wider range of ligands, including heparin sulphate proteoglycans and neural cell adhesion molecules as well as related sulphonated compounds (Green et al., 1996; ISSN 0265-9247). As early as 1994 research groups were investigating areas which would aid the design of synthetic sulphonated oligosaccharides aimed at improving the bioavailability of fibroblast growth factor when administered *in vivo* as a therapeutic agent (Coltrini et al., 1994; ISSN 0264-6021). Thus, Belford et al (1993) in Journal of Cellular Physiology 157 : 184-189 describes the ability of several animal, plant and bacterial derived polyanions as well as synthetic polyanions to compete with heparin for the binding of acidic fibroblast growth factor and correlates this with their ability to potentiate the mitogenic and neurotrophic actions of this factor. Dextran sulphate, kappa-carrageenan, pentosan sulphate, polyanethole sulphonate, heparin and fucoidin were shown to compete for the heparin binding site on a fibroblast growth

factor at relatively low concentrations (<50 μg/ml). The differential effects of these polyanions in potentiating the biological activities of fibroblast growth factor in relation to their ability to compete for the heparin-binding site of a fibroblast growth factor is discussed. Similarly, Hoover et al (1980) (in Circulation Research 47: 578: 583) studied the in vitro effects of heparin on the growth of rat aortic smooth muscle cells. The results showed that there was a highly specific interaction with regard to molecule and cell type i.e. other polyanions. The suggestion was that heparin and related dextran sulphate could in some way bind to certain factors responsible for cell growth and subsequent proliferation.

Non-enzymic glycosylation of basic fibroblast growth factor has recently been demonstrated to decrease the mitogenic activity of intracellular basic fibroblast growth factor. Loss of this bioactivity has been implicated in impaired wound healing and microangiopathics of diabetes mellitus. In addition to intracellular localisation, basic fibroblast growth factor is widely distributed in the extracellular matrix, primarily bound to heparin sulphate proteoglycans. Nissen et al (1999) measured the effect of non-enzymic glycosylation on basic fibroblast growth factor bound to heparin, heparin sulphate and related compounds (see Biochemical Journal 338: 637-642). When heparin was added to basic fibroblast growth factor prior to non-enzymic glycosylation, the mitogenic activity and heparin affinity of basic fibroblast

growth factor were nearly completely preserved. Heparin sulphate, low molecular mass heparin and the polysaccharide, dextran sulphate, demonstrated a similar protective effect.

The invention is now further described by reference to the following, non-limiting, examples (together with a comparative example).

Example 1

90 ml of water was added to 50 g of 40,000 molecular weight dextran and manually mixed to encourage the dextran to enter into solution. Afterwards the mixture was placed on a magnetic stirrer and allowed to mix continuously for 15 minutes or until the solution was clear and particle free.

5 g of urea were then added to the solubilised dextran and the mixture placed back on the magnetic stirrer for a further 15 minutes to ensure that the urea had entered into solution with the dextran. Finally, 10 ml of formalin (a 38% (w/v) aqueous solution of formaldehyde hydrate) providing 3.8 g of formaldehyde was added to complete the mixture which was again allowed to stir for 15 minutes. This mixture was the impregnated into knitted polyester grafts using vacuum techniques.

Gels were formed by placing the dextran impregnated grafts in an oven at 150°C for 2 hours. During this

time a cross-linking reaction was taking place. Grafts were washed for a minimum of four hours to ensure removal of any residual formaldehyde. Finished grafts were softened by exposure to 100% glycerol for 10 minutes followed by an alcohol wash to remove any excess glycerol. Grafts were then left to air dry.

Example 2

92 ml of water was added to 40 g of 40,000 molecular weight dextran and manually mixed to encourage the dextran to enter into solution. Afterwards, the mixture was placed on a magnetic stirrer and allowed to mix continuously for 15 minutes or until the solution was clear and particle free.

4 g of urea were then added to the solubilised dextran and the mixture placed back on the magnetic stirrer for a further 15 minutes to ensure that the urea had entered into solution with the dextran. Finally, 8 ml of formalin (38% aqueous solution of formaldehyde hydrate) providing 3.04 g formaldehyde was added to complete the mixture which was again allowed to stir for 15 minutes. Knitted polyester grafts were vacuum impregnated with this mixture.

Gels were formed by placing the grafts in an oven at 50°C for 12 hours. During this time a cross-linking reaction was taking place. Grafts were washed for a minimum of four hours to ensure removal of any residual formaldehyde. Finished grafts were softened by

exposure to 80% (v/v, in water) glycerol for 10 minutes followed by an alcohol wash to remove any excess glycerol. Grafts were then left to air dry.

Example 3 - Preparation of Dextran Blends

Table 1: Dextran/dextran sulphate crosslinked blends

Dextran (g)	Dextran Sulphate (g)	Urea (g)	Formaldehyde (ml)	Water (ml)
10	0	1	2	18
9	1	1	2	18
8	2	1	2	18
7	3	1	2	18
6	4	1	2	18
5	5	1	2	18

Dextran of molecular weigh 40,000 was weighed and the corresponding weight of dextran sulphate of similar molecular weight were added together. The correct level of water was added and the substances mixed thorougly until clear. The urea was mixed again before final addition of formaldehyde. The completed preparation was further mixed to ensure complete solubilisation. Gels were formed when the completed mix was placed in an oven for a specified time period. Samples were then washed for 3 hours in continuous running water.

Corresponding analysis (Dionex ion chromatography) to investigate the presence of sulphate groups in each of the samples showed significant detection of sulphation,

with least levels present in sample 1 (1 g of dextran sulphate) and most in sample 5 (5 g of dextran sulphate). It was proposed that the dextran sulphate had become entrapped within the network of cross-linked dextran chains to form an interpenetrating network with the potential to offer corresponding sulphation to the gels for subsequent attachment of growth factors. From the results various sulphanated gels could be prepared, see Examples 4 to 7.

Example 4

90 ml of water was added to a mixture of 30 g of 40,000 molecular weight dextran and 20 g of 40,000 molecular weight dextran sulphate and manually mixed to encourage the two forms of dextran to enter into solution with each other. Afterwards, the mixture was placed on a magnetic stirrer and allowed to mix continuously for 15 minutes or until the solution was clear and particle free.

5 g of urea was added and the mixture placed back on the magnetic stirrer for a further 15 minutes to ensure that the urea had entered into solution with the two dextran species. Finally, 10 ml of formaldehyde was added to complete the mixture, which was again allowed to stir for 15 minutes.

Gels were formed by placing the dextran mixture into an oven at 50°C for a minimum of 12 hours. During this time, a cross-linking reaction took place. The

subsequent dextran mixtures were washed for a minimum of 3 hours under continuous running water.

Example 5

90 ml of water was added to a mixture of 25 g of 40,000 molecular weight dextran and 25 g of 40,000 molecular weight dextran sulphate and manually mixed to encourage the two forms of dextran to enter into solution with each other. Afterwards the mixture was placed on a magnetic stirrer and allowed to mix continuously for 15 minutes or until the solution was clear and particle free.

5 g of urea was added and the mixture was placed back on the magnetic stirrer for a further 15 minutes to ensure that the urea had entered into solution with the two dextran species. Finally, 10 ml of formaldehyde was added to complete the mixture, which was again allowed to stir for 15 minutes.

Gels were formed by placing the dextran mixture into an oven at 50°C for a minimum of 12 hours. During this time a cross-linking reaction took place. The subsequent dextran mixtures were washed for a minimum of 3 hours under continuous running water.

Example 6

90 ml of water was added to a mixture of 30 g of 40,000 molecular weight dextran and 20 g of 40,000 molecular weight dextran sulphate and manually mixed to encourage

the two forms of dextran to enter into solution with each other. Afterwards the mixture was placed on a magnetic stirrer and allowed to mix continuously for 15 minutes or until the solution was clear and particle free.

5 g of urea was added and the mixture placed back on the magnetic stirrer for a further 15 minutes to ensure that the urea had entered into solution with the two dextran species. Finally, 10 ml of formaldehyde was added to complete the mixture, which was again allowed to stir for 15 minutes.

Gels were formed by placing the dextran mixture into an oven at 100°C for a minimum of 2 hours. During this time a cross-linking reaction took place. The subsequent dextran mixtures were washed for a minimum of 3 hours under continuos running water.

Example 7

90 ml of water was added to a mixture of 25 g of 40,000 molecular weight dextran and 25 g of 40,000 molecular weight dextran sulphate and manually mixed to encourage the two forms of dextran to enter into solution with each other. Afterwards the mixture was placed on a magnetic stirrer and allowed to mix continuously for 15 minutes or until the solution was clear and particle free.

5 g of urea was added and the mixture placed back on the magnetic stirrer for a further 15 minutes to ensure that the urea had entered into solution with the two dextran species. Finally, 10 ml of formaldehyde was added to complete the mixture, which was again allowed to stir for 15 minutes.

Gels were formed by placing the dextran mixture into an oven at 100°C for a minimum of 2 hours. During this time a cross-linking reaction took place. The subsequent dextran mixtures were washed for a minimum of 3 hours under continuos running water.

Example 8 - Resorption Rates

The resorption rate of sealant from dextran sealed grafts made according to Examples 1 and 2 were determined *in vitro* by incubating graft samples of known weight in buffer and weighing the grafts again after drying to measure the amount of sealant remaining. Urea formaldehyde cross-linked dextran was found to be hydrolysed at a rate comparable to the gelatin sealant of EP-B-0,183,365.

The hydrolysis profiles of urea-formaldehyde cross-linked dextran and formaldehyde cross-linked gelatin grafts are detailed in Table 2. Hydrolysis was performed at 37°C over a period of up to 4 weeks at 125 rpm.

Table 2

Comparative hydrolysis results for dextran and gelatin coated vascular grafts. The gelatin coated grafts were produced in accordance with Example 1 of EP-B-0,183,365.

Day	% gel degraded	
	Dextran	Gelatin*
0	0	0
3	5	30
6	15	70
12	25	95
28	95	100

*Comparative Example

Example 9 - Implantation

Grafts prepared according to Example 1 were implanted into the abdominal aorta of dogs for 2 weeks and 4 weeks respectively. Histological examination of the explanted devices showed that the sealant was resorbed as expected within 1 month and that the normal healing process was not adversely affected.

Claims

1 A bioresorbable sealant composition for coating a prosthetic graft, said composition comprising a polymer formed by cross-linking dextran molecules by formaldehyde and urea condensation.

2 The sealant as claimed in Claim 1, wherein said dextran molecules include naturally occurring dextran, hydrophilic hydroxyl group-containing derivatives of dextran or modified forms of dextran containing other reactive groups, for example dextran sulphate.

3 The sealant as claimed in Claim 1, wherein said naturally occurring dextran is provided by fermentation using *Leuconostoc mesenteroides* bacteria.

4 The sealant as claimed in any one of Claims 1 to 3 wherein the dextran molecules have a molecular weight of 30,000 to 60,000.

5 A method of producing a substantially non-porous graft by exposing at least one surface of a flexible material to a mixture of dextran, urea and formaldehyde, and incubating at temperatures of from 20°C to 250°C for a time sufficient for cross-linking of said dextran on said surface to take place.

6 The method as claimed in Claim 5 wherein the temperature is from 30°C to 200°C.

7 The method as claimed in either one of Claims 5 and 6 wherein said flexible material is a polyester knitted or woven fabric, or a PTFE-based material.

8 The method as claimed in Claim 7 wherein said fabric material is expanded PTFE.

9 The method as claimed in any one of Claims 5 to 8 further including the step of practising said cross-linked dextran by exposure of said coated surface to glycerol and, optionally, thereafter removing excess glycerol by alcohol rinsing.

10 A prosthetic graft impregnated or coated with the bioresorbable sealant as claimed in any one of Claims 1 to 4.

11 A method of forming polymerised dextran for use as a biodegradable coating for a prosthetic graft, said method comprising:

a) exposing a water-based solution of dextran to 2 to 25 (weight %) of urea and allowing the urea to enter into solution to form a mixture;

b) exposing the mixture of step a) to formaldehyde;

c) heating the mixture of step b) at temperatures between 20 to 250°C for a time sufficient to allow polymerisation to occur.

12 The method as claimed in Claim 11 wherein 50 to 100% (by weight) of formaldehyde, by reference to the weight of urea, is added.

13 The method as claimed in Claim 12 wherein 70 to 80% (be weight) of formaldehyde, by reference to the weight of urea, is added.

14 The method as claimed in any one of Claims 11 to 13 wherein the temperature is from 30°C to 200°C.

15 The method as claimed in any one of Claims 11 to 14 wherein said dextran has a molecular weight of 30,000 to 60,000.

INTERNATIONAL SEARCH REPORT

Intern ıal Application No
PCT/GB 00/03343

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 A61L27/34 A61L27/58

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 A61L A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)
EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 633 032 A (SUMITOMO ELECTRIC INDUSTRIES) 11 January 1995 (1995-01-11) column 5, line 28; claims; examples 1,2	1-15
Y	EP 0 183 365 A (COATS LTD J & P) 4 June 1986 (1986-06-04) cited in the application claims; examples	1-15
A	EP 0 742 020 A (NICEM LTD) 13 November 1996 (1996-11-13) claims; examples	1-15
A	US 5 851 229 A (DEPREKER JENNIFER ET AL) 22 December 1998 (1998-12-22) column 4, line 16 - line 46; claims	1-15

-/--

[X] Further documents are listed in the continuation of box C.

[X] Patent family members are listed in annex.

° Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
4 December 2000	11/12/2000

Name and mailing address of the ISA	Authorized officer
European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	ESPINOSA, M

2

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 00/03343

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 292 362 A (EATON ALEXANDER M ET AL) 8 March 1994 (1994-03-08) column 5, line 28; claims	1-15
A	US 4 902 290 A (WERNER HEINZ-HELMUT ET AL) 20 February 1990 (1990-02-20) cited in the application	
A	GB 854 715 A (AKTIEBOLAGET PHARMACIA) 23 November 1960 (1960-11-23) cited in the application	

2

INTERNATIONAL SEARCH REPORT

...ormation on patent family members

Interr ...al Application No
PCT/GB 00/03343

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0633032 A	11-01-1995	JP 7067895 A	14-03-1995
		AU 692445 B	11-06-1998
		AU 6596094 A	05-01-1995
		CA 2126608 A	26-12-1994
		US 5584877 A	17-12-1996
EP 0183365 A	04-06-1986	AT 83911 T	15-01-1993
		AU 569645 B	11-02-1988
		AU 5059385 A	05-06-1986
		CA 1249490 A	31-01-1989
		DE 3586941 A	11-02-1993
		DE 3586941 T	29-04-1993
		DK 551185 A	31-05-1986
		ES 548138 D	16-02-1988
		ES 8801577 A	16-04-1988
		GR 852872 A	03-04-1986
		IE 59421 B	23-02-1994
		JP 1585374 C	31-10-1990
		JP 2011258 B	13-03-1990
		JP 61135651 A	23-06-1986
		US 4747848 A	31-05-1988
EP 0742020 A	13-11-1996	JP 8294530 A	12-11-1996
		CN 1142974 A	19-02-1997
		US 5986168 A	16-11-1999
US 5851229 A	22-12-1998	AU 4414097 A	02-04-1998
		EP 0941131 A	15-09-1999
		WO 9810804 A	19-03-1998
US 5292362 A	08-03-1994	US 5209776 A	11-05-1993
		AT 183656 T	15-09-1999
		AU 8497991 A	02-03-1992
		CA 2087957 A	28-01-1992
		DE 69131556 D	30-09-1999
		DE 69131556 T	20-07-2000
		EP 0542880 A	26-05-1993
		ES 2137930 T	01-01-2000
		JP 6507376 T	25-08-1994
		WO 9202238 A	20-02-1992
US 4902290 A	20-02-1990	DE 3608158 A	17-09-1987
		AT 66126 T	15-08-1991
		BR 8701135 A	05-01-1988
		CA 1283505 A	30-04-1991
		DE 3772070 A	19-09-1991
		DK 127987 A	13-09-1987
		EP 0237037 A	16-09-1987
		FI 871065 A,B,	13-09-1987
		GR 3002895 T	25-01-1993
		JP 1051263 B	02-11-1989
		JP 1563185 C	12-06-1990
		JP 62258666 A	11-11-1987
		MX 165145 B	29-10-1992
		NO 870809 A,B,	14-09-1987
		US 4784659 A	15-11-1988
GB 854715 A		CH 413811 A	31-05-1966

Form PCT/ISA/210 (patent family annex) (July 1992)

INTERNATIONAL SEARCH REPORT

...ormation on patent family members

Intern ...al Application No
PCT/GB 00/03343

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 854715 A		DE 1418013 A SE 169293 A	17-10-1968